### POLYURETHANE ALIPHATIC FINISH PAINT



## **TECHNICAL DATA SHEET**

## DESCRIPTION:

It is two components, air drying coating based on acrylic polyol & cures with aromatic isocynate. This is ideal top coat for all structures in chemical environment. It is applied on interior side.

#### FEATURES:

- 1. Excellent Colour & Gloss retention.
- 2. Excellent flow & leveling properties.
- 3. Non yellowing & does not chalk easily.
- 4. When fully cured, it forms an extremely tough & abrasion resistance finish.
- 5. Compatible with Epoxy & Polyurethane undercoats.
- 6. Excellent UV resistance.
- 7. Good weathering durability.
- 8. Good resistance to splashes of mild solvents.

# APPLICATION AREAS:

- 1. This is suitable for use in Refineries, Petrochemical industries, Fertilizer plant, All type of chemical industries, Power plant, Transportation industries, etc.
- 2. It is specially formulated for concrete, plastic, metal, ferrous & nonferrous substrate, etc.

#### MIXING & APPLICATION:

- 1. Stir the base & hardner separately, if any settling observed in base loosen the settle material with the help of stirrer.
- 2. Mix hardner slowly in to base as per recommended mixing ratio. Stir well and make homogeneous mixture.
- 3. Adjust Spray viscosity by using recommended thinner (Application viscosity = 20-25 seconds).
- 4. Mix paint should be applying within pot life. After application Spray gun must be clean properly to avoid further damage.

# **POLYURETHANE ALIPHATIC FINISH PAINT**



# **TECHNICAL DATA SHEET**

# • TECHNICAL SPECIFICATIONS:

SR. NO.	TEST	SPECIFICATIONS
1	Application Area	M.S./CEMENT
2	Fineness Of Grind	7+
3	Colour	As per RAL & IS Shade Cards
4	Viscosity	90±30 Seconds By Ford Cup B4 @30°C
5	Specific Gravity	1.05±0.10
6	Drying Time Tack Free Hard Dry Full Cure	15 Min. 1 Hrs. Overnight 7 Days
7	Finish	Smooth & Uniform
8	Gloss	Glossy/Semi- Glossy/Matt/Egg-Shell
9	Dry Film Thickness	30-35 μ Per Coat
10	Covering Capacity (Practical)	6-7 sq.meter/liter
11	Scratch Hardness	2.50 Kg Passes
12	Mixing Ratio	Base : Hardner (By Volume) 4 : 1
13	Pot Life	4-5 Hrs.
14	Salt Spray Test (5% NaCl)	320 Hrs. Passes
15	Recommended Thinner	Sudarshan Make Thinner 155

#### POLYURETHANE ALIPHATIC FINISH PAINT



# **TECHNICAL DATA SHEET**

#### DIRECTIONS FOR USE:

## SURFACE PREPARARTION:

- 1. Surface must be dry, clean & free from contaminates.
- 2. Remove oil, grease, dirt & other contaminates by solvent cleaning.
- 3. Surface also clean by using shot blasting method.

## SAFETY PRECAUTIONS:

- 1. Avoid contact with skin & eyes.
- 2. Proper ventilation provide in application areas.
- 3. Use Mask, Safety Shoes, Goggles, and Hand Gloves.

#### STORAGE:

Paint must be store in cool, dry & ventilated place, stable under Normal condition.

#### SHELF LIFE:

12 Months from the date of manufacturing.

#### PACKING SIZE:

5L, 10L, 25L, etc.

#### DISCLAIMER:

The information provided in technical data sheet is to the best of our knowledge correct but not all inclusive & without warranty. It is the user's responsibility to conduct all necessary tests to confirm the suitability of any product or system for their intended use. No quarantee of result is implied since conditions of use are beyond our control.

(THIS IS COMPUTER GENERATED TECHNICAL DATA SHEET IT DOESN'T REQUIRED SIGNATURE)

F/SPC/87/00/1.2.2021